



ABN 98 000 869 367

563 Willoughby Rd. Willoughby 2068 Ph (02) 9958 5238 Fax (02) 9958 0838  
2 Lincoln St. Minto 2566 Ph (02) 9820 1144 Fax (02) 9603 2314  
188 Manns Road, West Gosford NSW 2250 Ph (02) 4322 0255 Fax (02) 4322 0266  
Unit 1 19 Boden Road Seven Hills NSW 2147 (02) 9674 7333 Fax (02) 9674 7377

## TECHNICAL INFORMATION SHEET

### ULTRABOND

**ULTRABOND** is light weight polyester compound cured by the addition of Methyl Ethyl Ketone Peroxide catalyst MEKP or M-60. It is produced from a flexible resin and thus accommodates some movement in the substrate.

It adheres well to polyester and many other surfaces. It is easily sanded.

#### TYPICAL PHYSICAL PROPERTIES

Uncured Adhesive

Specific Gravity	0.75
Gel time	2% Catalyst at 25°C 15 - 20 minutes
Colour	Grey
Consistency	Thick paste

#### SAFETY PRECAUTIONS

Ultrabond is a mixture of resin and light weight filler in styrene.

#### **Handling and safety details.**

Eye contact:	Wash eyes with copious amounts of clean water for at least 15 minutes and consult a physician.
Skin contact:	Wash off with soap and water.
Ingestion:	DO NOT induce vomiting. Give plenty of milk or water.

Refer M.S.D.S.